



A-Flex® Series

A-Flex® Muscovite Mica maintains a high aspect ratio of potassium aluminum silicate which exhibits superior brightness and purity.

A-Flex® Muscovite Mica industrial applications include:

Plastics – These miccas are excellent additives for plastics to improve flexural modulus, tensile strength, and dimensional stability and as an excellent extender for glass fiber.

Coatings – When used in coatings, mica platy structure imparts a barrier in the film to improve moisture resistance, chemical resistance, brush ability and promotes film adhesion.

	Product Description	MR80 - T3
Median Particle Size (d50)	Microns	60
% Passing	40 Mesh	100
	100 Mesh	98
	325 Mesh	54
Bulk Density	(lbs./ft ³)	14.30
	(g/cc)	0.22
Aspect Ratio		20-40

Typical Chemical Analysis (WT.) %		
Silicon Dioxide	SiO ₂	46
Magnesium Oxide	MgO	0.9
Aluminum Oxide	Al ₂ O ₃	31.6
Iron Oxide	Fe ₂ O ₃	4.9
Potassium Oxide	K ₂ O	10.5
Titanium Oxide	TiO ₂	0.2

Typical Properties	
True Density	2.85 g/cc
Melting Point	1,300°C
Moisture % (@100°C)	<0.4
pH	9.0
LOI @ 1,000 °C	<4.5
Mohs Hardness	2.5

Chemical Abstract Registry (CAS) No.: 12001-26-2

FDA: Arctic Minerals Mica products meet the FDA requirements of Title 21 CFR 175.105.5 Adhesive; 175.300 Resinous and Polymeric Coatings; 177.2600 Rubber articles intended for repeated use; 178.3297 Colorants for Polymers.

Contact us at: 812-283-6616

or Visit: ArcticMinerals.com

Information contained herein is to the best of our knowledge accurate, however, all recommendations or suggestions are made without our guarantee. Since the conditions of use are beyond our control, Arctic Minerals, LLC. disclaims any liability incurred in connection with the use of our products and information contained herein. No one is authorized to make any statement of recommendation not contained herein, and therefore, any such statement or recommendation so made shall not bind the company. Furthermore, nothing contained herein shall be as a recommendation to use any product in conflict with existing patents covering any material or its use. No license implied or in fact is granted herein under the claims of any patents.